

Łukasiewicz Research Network – Upper Silesian Institute of Technology

44-100 Gliwice, ul. Karola Miarki 12-14, POLAND Tel.: +48 32 23 45 251 E-mail: rm@git.lukasiewicz.gov.pl

CERTIFICATE OF ANALYSIS

IMZ 112B

REFERENCE MATERIAL LOW ALLOY STEEL

Analysis listed as percent by weight [% m/m]

С	0.195	Мо	0.043
Mn	0.43	V	0.045
Si	0.27	Nb	0.013
Р	0.022	Sn	0.15
S	0.016	N	0.0100
Cr	0.034	Al	(0.03)
Ni	0.046	Ti	(0.010)
Cu	0.055		

Values in brackets are informative

Certificate Number: IMZ 112B-221223

Certificate revision history on page 4

Analysis	С	Mn	Si	Р	S	Cr	Ni	Cu
1	0.187	0.413	0.233	0.0203	0.0160	0.0313	0.0413	0.0520
2	0.190	0.415	0.250	0.0203	0.0160	0.0330	0.0420	0.0527
3	0.191	0.427	0.257	0.0206	0.0163	0.0339	0.0443	0.0533
4	0.194	0.430	0.257	0.0207	0.0163	0.0340	0.0457	0.0543
5	0.194	0.432	0.263	0.0210	0.0164	0.0347	0.0457	0.0543
6	0.194	0.437	0.267	0.0213	0.0165	0.0347	0.0466	0.0547
7	0.195	0.437	0.270	0.0220	0.0166	0.0350	0.0473	0.0547
8	0.197	0.440	0.273	0.0230	0.0168	0.0356	0.0493	0.0556
9	0.197	0.447	0.278	0.0237	0.0169	0.0373	0.0493	0.0564
10	0.198	0.453	0.280	0.0256	0.0170		0.0500	0.0567
11	0.200		0.280					0.0577
12	0.202		0.280					
Average	0.1948	0.433	0.266	0.0218	0.0165	0.0344	0.0462	0.0547
SD	0.0042	0.012	0.014	0.0017	0.0003	0.0017	0.0030	0.0017
Certified value	0.195	0.43	0.27	0.022	0.016	0.034	0.046	0.055
C(95%)	0.0027	0.008	0.009	0.0012	0.0002	0.0013	0.0021	0.0012

Analysis	Мо	V	Ti*	Nb	AI*	Sn	N
1	0.0398	0.0417	0.0087	0.0115	0.03	0.137	0.0097
2	0.0403	0.0420	0.0095	0.0120		0.138	0.0099
3	0.0417	0.0437	0.0096	0.0120		0.147	0.0099
4	0.0420	0.0447	0.0101	0.0133		0.147	0.0101
5	0.0430	0.0450	0.0102	0.0137		0.147	0.0103
6	0.0433	0.0457	0.0106	0.0140		0.148	0.0104
7	0.0438	0.0465	0.0111	0.0151		0.150	0.0107
8	0.0448	0.0467	0.0111			0.164	
9	0.0450	0.0468				0.170	
10	0.0457	0.0480					
11	0.0460						
12							
Average	0.0432	0.0451	0.0101	0.0131		0.150	0.0101
SD	0.0021	0.0021	0.0008	0.0013		0.011	0.0003
Certified value	0.043	0.045		0.013		0.15	0.0100
C(95%)	0.0014	0.0015		0.0012		0.008	0.0003

^{* -} informative value

 $C(95\%) = (t \cdot SD)/\sqrt{n-1}$ - The half-width confidence interval, calculated for the 95 % confidence level, where t is the appropriate Student's t value, SD is the interlaboratory standard deviation and n is the number of acceptable mean values. For further information regarding the confidence interval for the certified value see ISO Guide 35:1989 section 4.

Certification Process: Both preparation of this Reference Material and certification process were prepared according to requirements of ISO Guide 31, ISO Guide 34 and ISO Guide 35. This Reference Material is in agreement with ISO Guide 30.

Chemical Analysis: Chemical analyses were carried out on chips prepared by milling of the certified portion of the bars. Single values in the above table are the means obtained by individual laboratories. The following methods were used for analysis:

C and S Mn	 high frequency infra-red absorption (HFIR); flame AAS, ICP-AES, photometric with potassium periodate, titrimetric arsenite-nitrite;
Si P	 ICP-AES, photometric as silicon-molybdenum blue, gravimetric; photometric as molybdenum blue, photometric as phosphovanadomolybdate, titrimetric, ICP-AES;
Cr	- flame AAS, ICP-AES, photometric with diphenylcarbazide, potentiometric, titrimetic;
Ni	- flame AAS, ICP-AES, photometric with dimethylglyoxime, potentiometric;
Cu Mo	 flame AAS, ICP-AES, photometric with diethyldithiocarbamate; flame AAS, ICP-AES, photometric with ammonium thiocyanate;
V	- flame AAS, ICP-AES, potentiometric, photometric;
Ti	- flame AAS, ICP-AES;
Ni	 ICP-AES, photometric with PAR, photometric with sulphochlorophenol S;
Al	 flame AAS, ICP-AES, photometric with aluminon, photometric with eriochromocyanin R;
Sn	- flame and GF AAS, ICP-AES;

The laboratories participating in the testing of this Reference Material were:

Huta Baildon, Katowice, Poland
Huta Częstochowa, Częstochowa, Poland
Huta Katowice S.A., Dąbrowa Górnicza, Poland
Huta Łabędy, Gliwice, Poland
Huta Ostrowiec S.A., Ostrowiec Świętokrzyski, Poland
Huta im. Tadeusza Sendzimira, Kraków, Poland
Huta Stalowa Wola - Zakład Hutniczy Sp. z o.o., Stalowa Wola, Poland
Instytut Metalurgii Żelaza, Gliwice, Poland
Hilger Analytical Ltd, Margate, Great Britain
Nova hut Ostrava s.p., Ostrava, Czech Republic
Ströhlein West Gmbh & Co., Kaarst, Germany
Třinecke Żelezarny, a.s., Třinec, Czech Republic
VSZ Labortest, spol. s r.o., Košice, Slovakia

- high temperature extraction.

Ν

Homogeneity: The homogeneity of this Reference Material was evaluated with the use of statistic parameters obtained during interlaboratory tests in 1996 and found acceptable. Optical emission spectrometry with spark excitation method was used.

Traceability: This Reference Material was tested with the use of optical emission spectrometry with spark excitation and was found compatible to the following CRMs: SS 431-435, SS 401-410, SS 50- 60, SS 456-460, SS 421-424, CKD 162A-171A.

Production of melt: This material was produced by Huta Baildon, Katowice. The melt was made in an open induction furnace and then ESR remelted.

Available form: Discs: 40 mm in diameter and 40 mm thick; chips: bottles 100g.

Intended use: This Reference Material is intended for use in optical emission and X-ray spectrometric methods (bulks sample) and also in classical wet methods, UV-Vis spectrometry, AAS, ICP-AES, C,S- and N- analyzers and other wet methods (chips). Caution: In optical emission spectrometry with spark excitation the central part of the surface of discs (approximately 5 mm) should be avoided because of possible segregation of the material.

Validity of certification: The certification of IMZ 112B is valid indefinitely provided this Reference Material is stored in dry place and in environment free from chemical or other aggressive vapours. Periodic recertification is not required. The certification is nullified if this Reference Material is damaged, contaminated or otherwise modified. Chips: if the contents of the bottle becomes changed (for example oxidized) or contaminated, the whole contents of bottle should be discarded.

Safety: This Reference Material and packing does not contain substances which can directly influence health.

Storage: This Reference Material should be stored in dry place and in environment free from chemical or other aggressive vapours.

Inquiries regarding this Reference Material should be directed to: rm@git.lukasiewicz.gov.pl

Approved by Director of the Institute

Prof. Dr. Hab. Eng. Adam Zieliński

Certificate issue date: 22 of December 2023

Certificate revision history:

22 December 2023 (titanium content changed into informative as a result of recertification analysis, editorial changes)

21 January 2021 (change of information regarding validity of certification, editorial changes);

21 February 2020 (Original certificate date).