

CERTIFICATE OF ANALYSIS

IMZ 3.60

CERTIFIED REFERENCE MATERIAL IRON ORE CONCENTRATE

Analysis listed as percent by weight [% m/m]

	Certified value	Uncertainty		Certified value	Uncertainty
Fe	63.36	± 0.22	Na ₂ O	0.027	± 0.004
Mn	0.098	± 0.002	FeO	25.37	± 0.25
TiO ₂	0.023	± 0.005	C	0.69	± 0.03
CaO	2.77	± 0.05	Pb	0.011	± 0.002
K ₂ O	0.039	± 0.002	Zn	0.28	± 0.02
S	0.074	± 0.002	Cu	0.007	± 0.001
P	0.019	± 0.001	Ni	0.0041	± 0.0006
SiO ₂	5.48	± 0.11	Cr	0.0077	± 0.0008
Al ₂ O ₃	0.356	± 0.008	Ba	0.0033	± 0.0006
MgO	0.64	± 0.02			

- the uncertainty bases on statistical evaluation of the contributions of the material homogeneity and the interlaboratory certification analysis

Informational values:

Co	(0.0011)	GOI	(0.30)
V	(0.0013)		

Certificate Number: IMZ 3.60-170225

Analysis	Fe	*	Mn	*	TiO ₂	*	CaO	*	K ₂ O	*	S	*	P	*	SiO ₂	*
1	63.00	4	0.095	1	0.020	1	2.86	1	0.032	3	0.066	2	0.0160	7	5.33	3
2	63.07	1	0.096	1	0.0210	7	2.85	1	0.033	1	0.07	2	0.0170	7	5.33	1
3	63.08	1	0.097	3	0.0211	3	2.85	1	0.038	3	0.0714	2	0.017	3	5.39	5
4	63.22	4	0.097	1	0.022	1	2.85	3	0.038	1	0.072	8	0.0173	3	5.437	1
5	63.24	4	0.0973	3	0.0223	3	2.815	3	0.038	3	0.072	5	0.0173	3	5.46	3
6	63.25	4	0.098	1	0.0244	3	2.765	3	0.039	3	0.073	1	0.0178	7	5.50	3
7	63.25	4	0.098	3	0.025	3	2.758	3	0.040	3	0.073	4	0.018	1	5.51	1
8	63.40	4	0.0986	3	0.026	1	2.74	3	0.040	3	0.074	2	0.018	3	5.52	1
9	63.40	4	0.100	3	0.026	1	2.73	1	0.043	3	0.0748	3	0.019	1	5.52	3
10	63.45	4	0.10	1	0.026	3	2.70	1			0.0756	2	0.020	1	5.54	1
11	63.47	1	0.10	3			2.69	1			0.076	8	0.020	1	5.56	3
12	63.49	3	0.102	1			2.640	3			0.080	2	0.0201	3	5.57	1
13	63.64	1									0.081	2	0.021	1	5.588	3
14	63.66	3											0.0210	3		
15	63.75	1														
16																
Average ¹	63.36		0.0982		0.0234		2.7715		0.0389		0.0735		0.0185		5.4793	
SD ²	0.2193		0.0019		0.0024		0.0725		0.0024		0.0025		0.0015		0.0784	
u characterization ³	0.07093		0.00068		0.0009		0.0262		0.0009		0.0009		0.00050		0.0263	
u homogeneity ⁴	0.08079		0.00073		0.00221		0.00751		0.00026		0.00056		0.00014		0.05110	
Certified value ⁵	63.36		0.098		0.023		2.77		0.039		0.074		0.019		5.48	
Expanded uncertainty ⁶	0.22		0.002		0.005		0.05		0.002		0.002		0.001		0.11	

Analysis	Al ₂ O ₃	*	MgO	*	Na ₂ O	*	FeO	*	C	*	Pb		Zn		Cu	
1	0.331	1	0.602	3	0.031	3	24.57	4	0.64	8	0.0091	3	0.242	3	0.0050	3
2	0.337	3	0.612	1	0.020	3	25.21	4	0.65	2	0.0092	3	0.257	1	0.0056	3
3	0.345	3	0.621	3	0.024	1	25.21	4	0.673	2	0.01	3	0.267	1	0.0068	1
4	0.35	3	0.621	10	0.025	3	25.23	4	0.678	2	0.0107	3	0.273	1	0.0069	3
5	0.35	3	0.63	3	0.026	1	25.43	4	0.68	2	0.012	3	0.276	3	0.0071	3
6	0.353	3	0.635	3	0.026	3	25.57	4	0.70	8	0.0143	1	0.280	1	0.0078	3
7	0.36	1	0.64	3	0.030	3	25.67	4	0.733	2			0.2848	3		
8	0.36	1	0.64	1	0.031	3			0.76	2			0.300	3		
9	0.36	1	0.64	1	<0,01	3							0.30	3		
10	0.363	7	0.64	1									0.328	3		
11	0.364	10	0.65	3									0.35	3		
12	0.37	3	0.67	1												
13	0.39	1	0.68	1												
14																
15																
16																
Average ¹	0.3564		0.6358		0.0267		25.373		0.6861		0.0099		0.2844		0.0061	
SD ²	0.0091		0.0180		0.0038		0.2747		0.0347		0.0011		0.0260		0.0013	
u characterization ³	0.0032		0.0063		0.00167		0.1217		0.0154		0.00055		0.00983		0.00068	
u homogeneity ⁴	0.00270		0.00496		0.00064		0.03652		0.00086		0.00014		0.00058		0.00009	
Certified value ⁵	0.356		0.636		0.027		25.37		0.69		0.011		0.28		0.007	
Expanded uncertainty ⁶	0.008		0.016		0.004		0.25		0.03		0.002		0.02		0.001	

Analysis	Ni		Cr		Ba		Co**		V**		GOI**		As		Cl	
1	0.0033	3	0.0046	3	0.0028	1	0.0005	3	0.0008	3	0.20	5	0.0006	3	0.0076	1
2	0.0037	3	0.0062	3	0.0032	3	0.0008	3	0.0012	1	0.24	5	0.001	3	0.0109	4
3	0.0042	3	0.0077	1	0.0033	3	0.0010	3	0.0013	3	0.278	5	0.0012	1	0.0135	3
4	0.0044	3	0.0077	3	0.0034	3	0.0014	1	0.0019	3	0.33	5	0.0019	3		
5	0.0045	1	0.008	1	0.0039	3	0.0016	3			0.35	5	0.0043	3		
6			0.0081	3							0.39	5				
7			0.0093	1												
8																
9																
10																
Average ¹	0.0044		0.0077		0.0033		0.0011		0.0013		0.298					
SD ²	0.0003		0.0007		0.0002		0.0004		0.0004		0.0715					
u characterization ³	0.00019		0.00031		0.00010		0.00025		0.0003		0.0366					
u homogeneity ⁴	0.00022		0.00024		0.00028		0.00026		0.00013		0.00852		0.00009		0.00025	
Certified value ⁵	0.0041		0.0077		0.0033											
Expanded uncertainty ⁶	0.0006		0.0008		0.0006											

* - analytical method used

** informative value

All values are based on recommendations of the ISO GUIDE 35:2017(E) standard:

1. Average is calculated according to Algorithm A (Guide clause A.2.3.4: Robust statistics);
2. Standard deviation is calculated according to Algorithm A (Guide clause A.2.3.4: Robust statistics);
3. Uncertainty of material characterization is based on the data obtained from the analysis performer by Network of competent labs (Guide clause 9.5) and calculated according to Guide clause B.5.2;
4. Uncertainty associated with homogeneity of material is calculated in agreement with Guide clause 7.11 (Uncertainty evaluation from homogeneity studies);
5. Certified value is the average value rounded to one or two significant digits of expanded uncertainty;
6. Expanded uncertainty is an geometric average of u characterization and u homogeneity multiplied by coverage factor $k = 2$.

Certification Process: Both preparation of this reference material and certification process were prepared according to requirements PN-EN 17034 and ISO GUIDE 35:2017(E).

Chemical Analysis: Chemical analyses were carried out on powder samples. Single values in the above table are the means obtained by individual laboratories. The following methods were used for analysis:

- 1 - wavelength dispersive x-ray fluorescence spectrometry (WD XRF),
- 2 - high frequency infrared absorption (HFIR),
- 3 - inductive coupled plasma atomic emission spectrometry (ICP OES),
- 4 - titrimetry,
- 5 - gravimetry,
- 7 - spectrophotometry,
- 8 - coulometry,
- 10 - flame atomic absorption spectrometry (FA AAS),

The laboratories participating in certification analysis:

- ArcelorMittal, Dąbrowa Górnicza, Poland, PCA 17025 – AB 1449,
- Liberty Steel Group, Ostrava, The Czech Republic, Accreditation Certificate No. 593/2017 by the Czech Accreditation Institute; ČSN EN ISO/IEC 17025:2005,
- ArcelorMittal, Maizières-lès-Metz Cedex, France,
- Envivorm a.s., Třinec, The Czech Republic; Testing Laboratory Nr 1371; Accreditation Certificate No. 219/2016 by the Czech Accreditation Institute; ČSN EN ISO/IEC 17025:2005,
- Institute for Certified Reference Materials, Jekaterinburg, Russia, accreditation RU.0001.510008,
- Instytut Metalurgii Żelaza, Gliwice, Poland; PCA 17025 – AB554,
- Lithea, Ltd. Brno, The Czech Republic,
- PJSC Elektrometallurgical Works Dnepropetsstal, Zaporozhe, Ukraine,
- U.S. Steel Košice, Slovakia; Slovenská národná akreditačná služba ISO/IEC 17025:2005, Reg. No. 026/S-010 and 026/S-011,

- Dunafer Labor Nonprofit Kft., Dunaújváros, Hungary; ISO/IEC 17025; NAH-2-0330/2016,
- Polcargo Medyka, Poland; PCA 17025 - AB 914.

Homogeneity: The homogeneity of this Reference Material was evaluated in accordance with guidelines of ISO GUIDE 35:2017(E) for subsample masses of at least 0,2g. Wavelength dispersive x-ray fluorescence spectrometry method, titrimetric method and high frequency infrared absorption method were used.

Traceability: This Reference Material was found traceable to the following CRMs: JK29, EU 680-1, SARM12, ICRM R38, ICRM 37, ICRM 39, ICRM 8/3, ICRM 5/6, ICRM 25/1, IMZ 2.61/1, IMZ 2.62/1, IPT23A, JSS814-1, JSS831-2, PI 3.20, PI3.21, PI3-23, PI3-24, PI3-25, IMZ 3.50, IMZ 3.51, IMZ.3.52, Č1-1-22, EU687-1, ASCRM 04, SARM11, JK28, Č1-1-21, Č1-1-24, Č1-1-25, DILL1105, DILL1131, DILL1132, DILL 1133, Č1-1-27, PI3-10, PI3-11, PI3-12, PI3-30, PI3-31.

Origin of the material: Ukraine (Dniepropietrovsk Concentrate)

Basic mineralogical composition:

magnetite Fe_3O_4	–	$72,0 \pm 1,3 \%$
hematite $\alpha\text{-Fe}_2\text{O}_3$	–	$15,1 \pm 0,8 \%$
quartz SiO_2	–	$4,1 \pm 0,5 \%$
calcite CaCO_3	–	$4,7 \pm 1,2 \%$
iron periclase $(\text{Mg,Fe})\text{O}$	–	$4,1 \pm 0,9 \%$

Available form: 100g of powder sample, grain size less than 0,2 mm

Intended use: This Reference Material is intended for use in determination of chemical composition of iron ores by x-ray fluorescence spectrometry, UV-Vis spectrometry, AAS, ICP-AES and C,S-analyzers and other wet methods. Chemical analyses should be carried out on samples dried at 105°C.

Validity of certification: The certification of IMZ3.60 is valid for 15 years - until March 2035, within the uncertainty specified provided this Reference Material is stored in accordance with the instructions given in this certificate (see Storage). The certification is nullified if this Reference Material is damaged, contaminated or otherwise modified.

Storage: This Reference Material should be stored in dry place and in environment free from chemical or other aggressive vapours and should be protected against vibration. If the contents become changed (for example oxidized) because of contamination, the whole contents of bottle should be discarded.

Safety: This Reference Material and packing do not contain substances which can directly influence health. Radioactivity less than 0.12 Bq/g equivalent of ^{60}Co .

Inquiries regarding this Reference Material should be directed to rm@git.lukasiewicz.gov.pl

Approved by
Director of the Institute

Prof. Dr. Hab. Eng. Adam Zieliński

Certificate issue date: 17 February 2025

Certificate revision history:

17 February 2025 (editorial change); 18 March 2020 (Original certificate date)