

SET-UP SAMPLE

IMZ S 16

HIGH ALLOY STEEL

Sample size: approx. fi 40 mm x 30 mm

Chemical composition. % m/m:

C	0.10	Ti	0.20
Mn	0.65	Cu	0.12
Si	1.3	Al	0.5
P	0.015	Zr	0.01
S	0.01		
Cr	14.3		
Ni	0.59		

Approved by
Director of the Institute

Prof. Dr. Hab. Eng. Adam Zieliński

Issue date: 02 July 2025

Revision history:

02 July 2025 (editorial changes)

December 2021 (Original document date)