

SET-UP SAMPLE

IMZ S 22

HIGH ALLOY STEEL

Sample size: approx. ϕ 45 mm, 23–35 mm high

Chemical composition, % m/m:

C	1.1	V	0.033
Mn	1.1	Ti	0.02
Si	0.94	Cu	0.03
P	0.01	Co	0.02
S	0.02	As	0.002
Cr	19.1	B	0.001
Ni	0.63		

Approved by
Director of the Institute

Prof. Dr. Hab. Eng. Adam Zieliński

Issue date: 27 November 2024

Revision history:

29 July 2024 (editorial changes)

December 2021 (Original document date)