

SET-UP SAMPLE

IMZ S 28

HIGH ALLOY STEEL

Sample size: approx. $\varnothing$ 40 mm, 30 mm high

Chemical composition, % m/m:

C	0.03	Ni	14.3
Mn	1.6	Mo	2.25
Si	0.75	Zr	0.005
P	0.01	B	0.005
S	0.01		
Cr	16.3		

Approved by
Director of the Institute

Prof. Dr. Hab. Eng. Adam Zieliński

Issue date: 27 November 2024

Revision history:

29 July 2024 (editorial changes)

December 2021 (Original document date)